

Don't Just Seal It, ConSeal It!

Butyl Rubber Sealant for Structures Requiring Watertight Seal with Ease of Access

Applications

CS-367 Entry Seal is a general purpose butyl rubber sealant for multiple applications that require a watertight seal but can be readily accessed. Not intended as a replacement for ConSeal CS-102 or other ConSeal performance rated sealants. **Not intended for use in expansion joints or joints that move.**



Sealing Properties

- Provides permanently pliable watertight joints.
- Remains pliable at all temperatures
- Non-oxidizing
- Provides long term or short term sealing solution
- Provides an air or leak resistant seal

Physical Properties & Chemical Composition

Description	Spec	CS-367
Color		Earhtone
Specific Gravity, 77°F (25°C)	ASTM D71	1.65-1.75
Hardness (150 gram cone penetration)	ASTM D217	50-60 dmm
Flash Point, C.O.C., °F	ASTM D92	350°F
Application temperature		0° to 100°F
Aging properties		Non-shrinking
Shelf life		2 years minimum

Installation Guidelines

The following procedures should be followed for optimum sealant performance.

- Clean the upper and lower joint surface with a stiff bristle brush.
 - Remove any dirt, debris, flashing, or concrete high points, which could keep the joint from coming together.
 - If necessary, a joint primer can be applied to improve sealant adhesion. Allow the primer to dry before placing sealant.
 - DO NOT PLACE ANY JOINTS WITHIN 12" OF A CORNER.
 - Join the sealant into one continuous strand by kneading the ends together where they meet. **Do not stretch the sealant.**
- A **minimum** compression of 50% is required. Greater than 50% compression is optimal. It may take 15-20 minutes for the sealant to fully compress. This will vary according to the ambient temperature and the weight being applied.
 - If necessary, CS-75 can be applied to one surface to secure the sealant. CS-75 is a water-based primer that dries tacky and must be applied at the time of the installation.
 - When using a CS-75, allow the primer to dry before placing sealant. CS-75 will normally be tacky within 15-20 minutes.

Reference Installation Instructions for **"Butyl Sealing Tapes"** for more detailed instructions.

Limited Warranty

This information is presented in good faith, but we cannot anticipate all conditions under which this information and our products, or the products of other manufactures in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combinations for their own purposes. It is the **users' responsibility** to satisfy himself as to the suitability and completeness of such information for this own particular use. We sell this product without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of this product, whether used alone or in combination with other products.