

SUBSTANCE	PREFORMED EXTRUDED SEALANTS				
	CS-101	CS-102	CS-202	CS-250	CS-440
10% Hydrochloric Acid	●	●	●	●	●
37% Sulfuric Acid	●	●	●	●	●
10% Sulfuric Acid	●	●	●	●	●
5% Acetic Acid	●	●	●	●	●
10% Nitric Acid	●	●	●	●	●
10% Potassium Hydroxide	●	●	●	●	●
10% Sodium Hydroxide	●	●	●	●	●
20% Sodium Carbonate	●	●	●	●	●
Bleach, concentrated	●	●	●	●	●
Chlorine	●	●	●	●	●
Toluene	●	●	●	●	●
MEK	●	●	●	●	●
Acetone	●	●	●	●	●
Isopropyl Alcohol	●	●	●	●	●
Mineral Spirits	●	●	●	●	●
n-heptane	○	○	○	○	○
Methanol	●	●	●	●	○
10% Salt Solution	●	●	●	●	●
3% Salt Solution	●	●	●	●	●
25% Sugar Water	●	●	●	●	●
Deionized Water	●	●	●	●	●
"Pool" Water pH 7.5	●	●	●	●	●
Lime Water	●	●	●	●	●
Diesel Exhaust Fuel	○	○	○	○	○
Diesel Fuel	●	●	●	●	●
Jet A Fuel	●	●	●	●	●
JP-4 Fuel	●	●	●	●	●
JP-8 Fuel	●	●	●	●	●
JP-10 Fuel	●	●	●	●	○
Kerosene	●	●	●	●	●
Gasoline	●	●	●	●	●
Hot Culinary Grease ¹	○	○	○	○	○
Karo Corn Syrup	●	●	●	●	●
Vegetable Oil	●	●	●	●	●
Motor Oil	●	●	●	●	●
Transmission Fluid	●	●	●	●	●
Brake Fluid	●	●	●	●	●
Antifreeze ²	●	●	●	●	●
Propylene Glycol	●	●	●	●	●
Glycerin	●	●	●	●	●
Fertilizers	●	●	●	●	●
Cleaning Detergent	●	●	●	●	○

¹Hot Culinary Grease (70°C): 100-g Crisco; 100-g vegetable oil; 50-g Caro Syrup; 100-g 50% sugar water; 10-g Dawn Detergent

²Antifreeze-ethylene glycol base

● CONTINUOUS SERVICE
Appropriate long-term application.
Substance has negligible to no effect on product.

● LIMITED SERVICE EXPOSURE*
Substance has some effect on product.
*Contact Concrete Sealants, Inc. for service options.

● NOT RECOMMENDED
Substance affects performance of product.

○ NOT TESTED
Results not yet available.

DISCLAIMER: This document is to assist users to understand the proper use of ConSeal's products. Field conditions may vary from those simulated for this test and may impact product performance. Concrete Sealants, Inc. is not responsible for variable environmental conditions and does not warranty any improper use of its products. *Contact Concrete Sealants, Inc. to discuss options for your specific application.*