

# Butyl Rubber Sealant for Structures Requiring Watertight Seal with Ease of Access



## PRODUCT APPLICATIONS

CS-367 Entry Seal is a general purpose butyl rubber sealant for multiple applications that require a watertight seal but can be readily accessed. Not intended as a replacement for ConSeal CS-102 or other ConSeal performance rated sealants. **Not intended for expansion joints or joints that move.**

## SEALING PROPERTIES

- Provides permanently pliable watertight joints.
- Low to high temperature workability: 0°F to 120°F (-18°C to +49°C)
- Remains pliable at all temperatures.
- Non-shrinking, non-oxidizing.
- Provides long term or short term sealing solution.
- Provides an air or leak resistant seal.
- 2-year minimum shelf life.

## PHYSICAL PROPERTIES & CHEMICAL COMPOSITION

Description	Test Method	CS-367
Color		Gray
Specific Gravity, 77°F (25°C)	ASTM D71	1.65–1.80
Penetration, cone 77°F (25°C), 150 gm, 5 sec.	ASTM D217	50–60 dmm
Flash Point, C.O.C.	ASTM D92	350°F (177°C)

## IMMERSION TESTING

**30-Day Immersion Testing:** No visible deterioration when tested in 5% Caustic Potash (Potassium Hydroxide), 5% Hydrochloric Acid, 5% Sulfuric Acid, and 5% saturated Hydrogen Sulfide.

**One Year Immersion Testing:** No visible deterioration when tested in 5% Formaldehyde, 5% Formic Acid, 5% Sulfuric Acid, 5% Hydrochloric Acid, 5% Sodium Hydroxide, 5% Hydrogen Sulfide, and 5% Potassium Hydroxide.

## INSTALLATION GUIDELINES

The following procedures should be followed for optimum sealant performance.

- Clean the upper and lower joint surface with a stiff bristle brush.
- Remove any dirt, debris, flashing, or concrete high points, which could keep the joint from coming together.
- ConSeal recommends the use of surface primers, as primers improve adhesion. When using a primer, allow the primer to dry before placing sealant.
- ConSeal primers are specifically designed for use with ConSeal products. Contact ConSeal for the best primer for the projects specific application.
- **DO NOT PLACE ANY JOINTS WITHIN 12" OF A CORNER.**
- Join the sealant into one continuous strand by kneading the ends together where they meet. **Do not stretch the sealant.**
- A minimum compression of 50% is required. Greater than 50% compression is optimal. It may take 15-20 minutes for the sealant to fully compress depending on the ambient temperature and the weight being applied.

Reference Installation Instructions for “Butyl Sealing Tapes” for more detailed instructions.

## LIMITED WARRANTY

This information is presented in good faith, but we cannot anticipate all conditions under which this information and our products, or the products of other manufactures in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combinations for their own purposes. It is the users' responsibility to satisfy himself as to the suitability and completeness of such information for this own particular use. We sell this product without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of this product, whether used alone or in combination with other products.

© 2025 CONCRETE SEALANTS, INC.

CONCRETE SEALANTS, INC. | 9325 STATE ROUTE 201, TIPP CITY, OH 45371, USA | [WWW.CONSEAL.COM](http://WWW.CONSEAL.COM)

USA | CANADA | +1.800.332.7325 | INTERNATIONAL | +1.937.845.8776

VERSION: 24-OCTOBER-2025



CONCRETE SEALANTS, INC.  
ISO 9001:2015 REGISTERED